

Product Profile


Identification

Product Name: Poly(styrene-b-methylmethacrylate)

Product Lot Number: P18585-R-SMMA

CAS #: 25034-86-0

Product Chemical Architecture:



Composition:

| | |
|-------------------------------------|-----------------------|
| Composition (S-b-MMA) | 9,000-b-13,000 |
| MMA mole% | 58.0 |
| Tacticity (atac, iso, syn) | > 78% syn |
| Mw/Mn | 1.06 |
| dn/dc (mL/g) in THF at 30 °C | 0.136 |

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

| | | | |
|---------|------------------------|-------------------|---|
| THF | √ | DMF | √ |
| Alcohol | X | CHCl ₃ | √ |
| Toluene | Depends on composition | Water | X |


Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.

Chromatogram Plot

P18585R-SMMA



Molecular Weight Averages

| Peak | Mp (g/mol) | Mn (g/mol) | Mw (g/mol) | Mz (g/mol) | Mz+1 (g/mol) | Mv (g/mol) | PD |
|--------|------------|------------|------------|------------|--------------|------------|-------|
| Peak 1 | 25955 | 20720 | 22023 | 23207 | 24243 | 23122 | 1.063 |

B. NMR (¹H NMR) of SMMA

SMMA sample was dissolved in CDCl₃. ¹H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.

