

Product Profile


Identification

Product Name: Poly(styrene-b-methylmethacrylate)

Product Lot Number: P4498-R-SMMA

CAS #: 25034-86-0

Product Chemical Architecture:



Composition:

Composition (S-b-MMA)	40,000-b-236,000
MMA mole%	85.4
Tacticity (atac, iso, syn)	PMMA > 78% syn
Mn (g/mole)	277,000
Mw (g/mole)	300,000
Mw/Mn	1.08
dn/dc (mL/g) in THF at 30 °C	0.104

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	X	CHCl ₃	√
Toluene	Depends on composition	Water	X

Validation of Architecture


A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1% (v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.

Agilent GPC/SEC Software

P4498

Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	318392	276508	299761	317800	332831	317326	1.084

B. NMR (^1H NMR) of SMMA in CDCl_3 , 500 MHz

