

# Product Profile


## Identification

**Product Name:** Poly(styrene-b-methylmethacrylate)

**Product Lot Number:** P7571-R-SMMA

**CAS #:** 25034-86-0

**Product Chemical Architecture:**



**Composition:**

<b>Composition (S-b-MMA)</b>	<b>86,000-b-14,000</b>
<b>MMA mole%</b>	<b>14.3%</b>
<b>Tacticity (atac, iso, syn)</b>	<b>PMMA &gt; 78% syn</b>
<b>Mn (g/mole)</b>	<b>100,000</b>
<b>Mw (g/mole)</b>	<b>106,000</b>
<b>Mw/Mn</b>	<b>1.06</b>
<b>dn/dc (mL/g) in THF at 30 °C</b>	<b>0.171</b>

## Method of Synthesis

The polymer is synthesized by anionic polymerization process.

**Solubility in different solvents:**

THF	√	DMF	√
Alcohol	X	CHCl <sub>3</sub>	√
Toluene	Depends on composition	Water	X


## Validation of Architecture

### A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5μm-10μm, 10<sup>5</sup>-10<sup>6</sup>Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.

## P7571

### Chromatogram Plot



### Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	105480	100414	106404	112181	118298	111173	1.06

### B. NMR (<sup>1</sup>H NMR) of SMMA

SMMA sample was dissolved in CDCl<sub>3</sub>. <sup>1</sup>H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.

