

# Product Profile


## Identification

**Product Name:** Poly(deuterated styrene (d8)-b-methylmethacrylate)

**Product Lot Number:** P44703-dPSMMA

**CAS #:** 25034-86-0 (protonated analog)

**Product Chemical Architecture:**



**Composition:**

<b>Composition (dPS-b-MMA)</b>	<b>7,000-b-74,000</b>
<b>MMA mole %</b>	<b>91.3%</b>
<b>Tacticity (atac, iso, syn)</b>	<b>PMMA &gt; 78% syn</b>
<b>Mw/Mn</b>	<b>1.40</b>
<b>dn/dc (mL/g) in THF at 30 °C</b>	<b>0.105-0.135 depends on its composition</b>

## Method of Synthesis

The polymer is synthesized by anionic polymerization process.


**Solubility in different solvents:**

THF	√	DMF	√
Alcohol	X	CHCl <sub>3</sub>	√
Toluene	Depends on composition	Water	X

## Validation of Architecture

### A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10<sup>5</sup>-10<sup>6</sup>Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



B. NMR ( $^2\text{H}$ NMR) of d8 styrene used  
 $^2\text{H}$  (deuterium) NMR spectrum (500 MHz,  $\text{CHCl}_3$ ):

