

Product Profile


Identification

Product Name: Poly(styrene-b-ethylene oxide)

Product Lot Number: P44794-SEO

CAS #: Not Available

Chemical Architecture:



Composition:

Composition (S-b-EO)	16,000-b-25,000
EO mole%	61
Mn (g/mole)	41,000
Mw (g/mole)	42,000
Mw/Mn	1.01
dn/dc (mL/g) in THF at 30 °C	0.113

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	X	CHCl ₃	√
Toluene	√	Water	X


Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	43804	40976	41527	42038	42509	41850	1.013

B. NMR (¹H NMR) of SMMA

SMMA sample was dissolved in CDCl₃. ¹H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.

