


Product Profile

Identification

Product Name: Poly(glycidyl methacrylate)

Product Lot Number: P8452-R-GMA

Product Chemical Architecture:




Composition:

Mn (g/mole)	19,000
Mw (g/mole)	20,500
Mw/Mn	1.09
dn/dc (mL/g)	0.084 in THF

Method of Synthesis

Poly(glycidyl methacrylate) is obtained by living anionic /GTP polymerization of glycidyl methacrylate. The reaction scheme used for the polymer synthesis is shown below:




Solubility in different solvents

THF	√	Alcohol	X
1,4-dioxane	√	CHCl ₃	√

Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC- Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90o and LS 15o) and three columns (PLgel, 7.5x300 mm, 5μm-10μm, 105-106Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



B. DSC thermogram for the polymer:

