


Product Profile

Identification

Product Name: Poly(styrene-b-ethylene oxide)

Product Lot Number: P44820-SEO

CAS #: Not Available **Product Chemical Architecture:**



Composition:

Composition (S-b-EO)	28,000-b-42,000
EO mole%	60
Mn (g/mole)	70,000
Mw (g/mole)	73,000
Mw/Mn	1.03
dn/dc (mL/g) in THF at 30 °C	0.115

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	X	CHCl ₃	√
Toluene	√	Water	X

Validation of Architecture


A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



Chromatogram Plot

P44820



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	81155	70457	72815	74867	76634	0	1.033

B. NMR (¹H NMR) of SMMA

SMMA sample was dissolved in CDCl₃. ¹H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.

