


Product Profile

Identification

Product Name: Poly(styrene-b-ethylene oxide)

Product Lot Number: P44840-SEO

CAS #: Not Available **Product Chemical Architecture:**



Composition:

Composition (S-b-EO)	3,000-b-7,000
EO mole%	74
Mn (g/mole)	10,000
Mw (g/mole)	10,000
Mw/Mn	1.01
dn/dc (mL/g) in THF at 30 °C	0.098

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	√	CHCl ₃	√
Toluene	√	Water	√


Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.

Chromatogram Plot

P44840




Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	10179	9666	9781	9888	9986	9854	1.012

B. NMR (^1H NMR) of SEO

SMMA sample was dissolved in CDCl_3 . ^1H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.



124 avenue Avro, Dorval (Montreal)
Quebec H9P 2X8 Canada
Phone : +1-514-421-5517 or +1-514-421-5506
support@polymersource.com
www.polymersource.ca