

Product Profile


Identification

Product Name: Poly(ethylene oxide-b-lactide)

Product Lot Number: P5497-R-EOLA

CAS #: Not Available

Product Chemical Architecture:



Composition:

Composition (EO-b-LA)	10,000-b-1,000
EO mole%	93
Mw (g/mole)	30,000
Mw/Mn	1.23
dn/dc (mL/g) in THF at 30 °C	0.018

Method of Synthesis

The polymer is synthesized by anionic polymerization and coordination polymerization processes.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	√	CHCl₃	√
Toluene-Hot	√	Water	√

Validation of Architecture


A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5µm-10µm, 10⁵-10⁶Å). THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



P5497

Chromatogram Plot




Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	26542	24293	29973	36091	42026	34222	1.234

B. NMR (H¹NMR) of EOLA

EOLA sample was dissolved in CDCl₃. ¹H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.



124 avenue Avro, Dorval (Montreal)
Quebec H9P 2X8 Canada
Phone : +1-514-421-5517 or +1-514-421-5506
support@polymersource.com
www.polymersource.ca