


Sample Name: Poly(styrene-co-1,2-butadiene-co-1,4-butadiene), random

Sample #: P44505-SBdran

Structure:



Composition:

Mn x 10 ³ PS-co-PBd	PDI
40.0	1.2
T _g for random polymer -22°C	
Styrene (mol%): 80.0	

Synthesis Procedure:

Random Copolymer Poly(styrene-co-butadiene) is prepared by radical polymerization of styrene and butadiene.

Characterization:

The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Solubility:

Random Copolymer Poly(styrene-co-butadiene) is soluble in CHCl₃, THF, DMF, toluene and precipitated out from methanol.

SEC elugram of the random copolymer:



¹H NMR of Copolymer in CdCl₃:



Thermogram of the sample:

