


Sample Name: Deuterated Polystyrene (d₈)

Sample #: P11350-dPS

Structure:




Composition:

Mn x 10 ³	PDI
390.0	1.09

Synthesis Procedure:

Deuterated polystyrene-d₈ is obtained by living anionic polymerization of styrene-d₈ as illustrated below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.


Solubility:

Deuterated polystyrene-d₈ is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC of Homopolymer:

Sample ID: P11350-dPS

Concentration (mg/mL)	3.4290
Sample dn/dc (mL/g)	0.1700
Method File	PS80K-Mar-2013-0002.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn (Da)	Mw (Da)	Mp (Da)	Mw/Mn	IV (dL/g)
P11350_2013-03-04_13:41:13_01.vdt	390,028	422,811	400,742	1.084	1.5828

