


Product Profile

Identification

Product Name: Poly(dl-lactide)-b-poly(methacrylic acid-co-3-acrylamidophenylboronic acid)

Sample #: P45707-LAMAAPBA


Structure:




Composition:

Mn x 10 ³ PDLLA-b-MAAPBA	Mw/Mn (PDI)	Dp of copolymer by HNMR	Dp of copolymer by HNMR
5.0-b-23.0	1.4	In DMSO PDLLA ₇₀ -b-MAA ₂₁₅ PBA ₂₇	In DMSO+CD ₃ Cl PDLLA ₇₀ -b-MAA ₂₂₇ PBA ₂₆
		In DMSO+ a drop of Cd ₃ OD PDLLA ₇₀ -b-MAA ₂₄₀ PBA ₂₆	

Method of Synthesis. 2 step synthesis 1. RAFT macroinitiator of Poly(dl LA) of Mn 5000



2. Reaction of RAFT macroinitiator with MAA and PBA monomer **in Dioxan** with trace amount of water



Solubility in different solvents: depending on the compositions

THF	X	Methanol	√	Acetone	×
CHCl ₃	X	DMSO	√	Aceton:Methanol 5:5	√

Purification of Polymer By Soxhlet in acetone: to remove any traces amount of PDLLA and unreacted RAFT and traces amount of MAA and PBA monomer.

A. Gel Permeation Chromatography (GPC), SEC- Profile




B. HNMR of DILA RAFT



	<u>Chemical shift</u> <u>C-(H)</u>	<u>C(CH3)</u>	<u>Calculated</u> <u>Mn</u>
<u>In acetone</u>	<u>5.43</u>	<u>1,53</u>	<u>4,800</u>
<u>In CdCl3</u>	<u>5.05</u>	<u>1.60</u>	<u>5,500</u>
<u>In DMSO</u>	<u>5.43</u>	<u>1.45</u>	<u>4,000</u>
			<u>Average</u> 5,000

D. HNMR of Block copolymer

1. Run from d6 DMSO



E. TGA of the polymer run at 10 °C heating rate:

