


## Sample Name: Poly(t-butyl acrylate)

Sample #: **P11415-tBuA**

### Structure:



### Composition:

Mn x 10 <sup>3</sup>	PDI
111.0	2.8

### Synthesis Procedure:

Poly(t-butyl acrylate) is obtained by anionic process.


### Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

### Solubility:

Poly(t-butyl acrylate) is soluble in THF, hexanes (low MW), toluene and CHCl<sub>3</sub>. This polymer precipitates from ethanol and methanol containing 10-15% water.

T<sub>g</sub> of poly t-butyl acrylate as function of molecular weight




### References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53

### SEC of Sample:

Sample ID: P11415-tBuA

Concentration (mg/mL)	6.0499
Sample dn/dc (mL/g)	0.0512
Method File	PS80K-Mar-2013-0002.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P11415-tBuA_01.vdt	110,784	318,553	161,134	2.875	0.6209

