


**Sample Name:**  
**Poly(Styrene-b-1-Adamantyl methacrylate)**

**Sample #:** P13248-SADMMA  
**Structure:**



**Composition:**

Mn x 10 <sup>3</sup> PS-b-ADMMA	PDI
6.0-b-7.5	1.25
Microstructure for ADMMA	Syndio:hetero:iso Rich in heterotactic
T <sub>g</sub> for PS block: Not distinct	T <sub>g</sub> for PADMMA block: 143°C

**Synthesis Procedure:** Prepared by controlled radical process.

**Characterization:**


An aliquot of the anionic poly(ADMA) block was terminated before addition of MMA monomer and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T<sub>g</sub>) of the sample has been considered.

**Solubility:**


Polymer is soluble in THF, CHCl<sub>3</sub>, toluene and dioxane. The polymer precipitates from hexanes, methanol and ethanol.

**<sup>1</sup>H-NMR Spectrum of the block copolymer:**



**SEC of the block copolymer:**

**P 13248-SADMMA**



Size exclusion chromatography:

- Poly(Styrene block), M<sub>n</sub>=6000, M<sub>w</sub>=7500, PI=1.25
- Block Copolymer PS(6000)-b-PADMMA(7500), PI=1.25 composition from H NMR

**DSC thermogram for ADMMA block:**

