


Sample Name:

Poly(dimethylsiloxane-b-POSSisobutylmethacrylate)

POSSisoButylMA: 3-(3,5,7,9,11,13,15-heptaisobutylpentacyclo[9.5.1.1_{3,9}.1_{5,15}.1_{7,13}]octasiloxan-1-yl)propylmethacrylate

Sample #: P14013-DMSPOSSisoBuMA

Structure:



Composition:

Mn x 10 ³ PDMS-b- POSSisoBuMA	PDI
5.0-b-4.5	1.13

Synthesis Procedure:

Polymer is synthesized by controlled radical polymerization process.



Purification of the polymer:

The obtained polymer dissolved in CHCl₃/toluene and pass through the column packed with silica. The polymer was recovered by precipitation in cold ether/ethanol mixture.


Solubility:

Polymer is soluble in CHCl₃, THF and toluene. The polymer precipitated out from hexane.

Chemical Shifts:




HNMR of the Product:



SEC of the block copolymer:

P14013-DMSPOSSisoBuMA



— Poly(DMS): M_n=5000, M_w=6300, M_w/M_n=1.05

— Block Copolymer PDMS(5000)-b-POSSisoBuMA(4,500), M_w/M_n=1.13

Thermal analysis of the P14013-DMSPOSSisoBuMA

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Melting and crystallization curve for the sample

The melting temperature (T_m) was taken as the maximum of the endothermic peak whereas the crystallization temperature (T_c) was considered as the minimum of the exothermic peak.

Thermal analysis results at a glance:

Sample	T_m (°C)	T_c (°C)	T_g (°C)
DMS block	Not distinct		
POSSMA block	96	53	-

Melting curves for POSSBuMA:



Crystallization curves POSSisoBuMA block:

