


Sample Name: **Polystyrene**

Sample #: **P14149B-S**

Structure:




Composition:

Mn x 10 ³	PDI
5.0	1.40

Synthesis Procedure:

Polystyrene is obtained by free radical polymerization as illustrated below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:

Polystyrene is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC of the polymer:

P14149B-S

