


**Sample Name:** Random copolymer of Poly (styrene–co–4-vinyl pyridine–co-[poly (ethylene oxide–b–propylene oxide–b–ethylene oxide)] methacrylate)

**Sample #:** P14439-S4VPEOPOEOran

**Structure:**



**Composition:**

Mn × 10 <sup>3</sup>	PDI
108.0	1.3

S: 4VP: ratio	19:81
4VP:EOPOEO ratio	16:84
S:4VP:EOPOEO ratio After normalization	10:45:45
Macromonomer Lot # P10873 EOPOEO-MA 0.30-b-1.7-b-0.600	Dp; 7-b-29-b-14

**Characterization:**

The polymer analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy.



**Solubility:**

The polymer is soluble in acetone, DMF, methanol. It precipitates from, ether and hexane.


**Thermal analysis**

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 20°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T<sub>g</sub>).


**HNMR of EOPOEO Macromonomer: EOPOEO**  
**First Block mPEG**




**HNMR of EOPOEO-MA end functional**



### HNMR of the random copolymer:




### DSC thermogram for the polymer:



### SEC of the copolymer:

P14439-S4VPEOPOEO ran  
Run in DMF at 60 oC



$M_n=108,000$ ,  $M_w=140,000$ ,  $\text{PI}=1.3$