


Sample Name:

Poly(styrene-*b*-N-isopropyl acrylamide)

Sample #: P14955-SNIPAM

Structure:



Composition:

$M_n \times 10^3$ S- <i>b</i> -NIPAM	M_w/M_n (PDI)
2.0- <i>b</i> -5.9	1.1

Polystyrene content: 27 mol %

Synthesis Procedure:

Poly(styrene-*b*-N-isopropyl acrylamide) is prepared by RAFT polymerization with sequence addition of styrene followed by N-isopropyl acrylamide. The polymer was obtained by precipitating into cold diethyl ether/hexane.

Characterization:

The final block copolymer composition and molecular weight was calculated from $^1\text{H-NMR}$ spectroscopy by comparing the peak area of the aromatic protons on styrene between about 6.5-7.5 ppm with the proton of NCH on NIPAM at 3.9 ppm. The PDI of block copolymer is determined by SEC.


Thermal analysis

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 15°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Solubility:

Poly(styrene-*b*-N-isopropyl acrylamide) block copolymer is soluble in DMF.

$^1\text{H NMR}$ spectrum of the first block polystyrene




$^1\text{H NMR}$ spectrum of the block copolymer PS-*b*-NIPAM



SEC elugram of block copolymer

SAMPLE ID: P14955-2-SNIPAM

Conc (mg/mL)	4.1105
dn/dc (mL/g)	0.1000
Method	ps80k-21Jan2016-DMF-0.000.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS



Sample	M_n	M_w	M_p	M_w/M_n	IV
P14953-2_01.vdt	7,974	8,535	8,672	1.070	0.0784