


Sample Name: Polystyrene-Broad Distribution

Sample #: P15003-S

Structure:



Composition:

Mn x 10 ³	PDI
128.0	1.3

Synthesis Procedure:

Polystyrene is obtained by free radical polymerization of styrene.

Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:

Polystyrene is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC of Homopolymer

P15003-S

