


**Sample Name:** Poly(acrylic acid -b- N-isopropylacrylamide)

**Sample #:** P16016A-AANIPAM

**Structure:**



**Composition:**


Mn x 10 <sup>3</sup> PAA-b-PNIPAM	3.5-b-1.3
--------------------------------------	-----------

PDI	1.1
-----	-----

DP of each block: PAA-b-PNIPAM	49-b-11
-----------------------------------	---------

### Synthesis Procedure:

Poly(acrylic acid-b-N-isopropylacrylamide) is prepared by RAFT polymerization and sequential addition of acrylic acid monomer and N-isopropylacrylamide monomer. The CTA used in polymerization is shown as follows:




### Characterization:


The molecular weight, polydispersity and composition of polymer were characterized by SEC and <sup>1</sup>H NMR.

**Solubility:** Poly(acrylic acid -b- N-isopropylacrylamide) is soluble in MeOH and water.

### <sup>1</sup>H-NMR Spectrum of the PAA-RAFT macroinitiator in DMSO-d6



### <sup>1</sup>H NMR spectrum of the diblock copolymer PAA-b-PNIPAM in MeOH-d4




SEC of first block was carried out to convert PAA into poly n-Butylacrylate to determine molecular weight of the poly acrylic acid.

### SEC elugram of the first block of poly(n-butyl acrylate):

P16016-nBuA

Conc (mg/mL)	17.7332
din/dc (mL/g)	0.0650
Method	ps80k/May2016-0002.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P16016-nBuA_01(59).vdt	6,947	7,544	7,157	1.086	0.1350