



Product Profile


Identification

Product Name: Poly(ϵ -Caprolactone)

Product Lot Number: P18183-CL

CAS #: 24980-41-4

Chemical Architecture:



Composition:

Mn (g/mole)	11,000
Mw (g/mole)	17,500
Mw/Mn	1.6
dn/dc (mL/g) in THF at 30 °C	0.030

Method of Synthesis

The polymer is synthesized by ring opening polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	X	CHCl ₃	√
Toluene	√	Water	X

Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:


Molecular weights were determined by Agilent Technologie 1260 Infinity II GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LS 15°) and three columns (PLgel, 7.5x300 mm, 5 μ m-10 μ m, 10⁵-10⁶Å).

THF (stabilized BHT) with 1%(v/v%) TEA was the eluent. The flow rate was 1.0 ml/min.



Polymer Source,™ Inc.

P18183-CL




Size exclusion chromatography result:

— $M_n=11,000$, $M_w=17,500$ $PI=1.6$ (M_n calculated by HNMR)

B. NMR (1H NMR) of CL

CL sample was dissolved in $CDCl_3$. 1H NMR spectra was determined using a 500 MHz. Bruker Avance III spectrometer.



124 avenue Avro, Dorval (Montreal)
Quebec H9P 2X8 Canada
Phone : +1-514-421-5517 or +1-514-421-5506
support@polymersource.com
polymersource.ca



Thermal analysis of the sample

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Melting and crystallization curve for the sample

The melting temperature (T_m) was taken as the maximum of the endothermic peak where as the crystallization temperature (T_c) was considered as the minimum of the exothermic peak.

Thermal analysis results at a glance

T_m (°C)	T_c (°C)	T_g (°C)
44	17	Not distinct

Melting curve for the CL sample:



Crystallization curve for the CL sample:

