


Sample Name: Poly(styrene-b-2-vinyl pyridine)

Sample #: P18226-S2VP

Structure:




Composition:

Mn x 10 ³ S-b-2VP	PDI
30.0-b-8.5	1.06
T _g for 2VP block: Not distinct 95°C for 100k homopolymer)	T _g for PS block: 104 °C

Synthesis Procedure:

Poly(styrene-b-2-vinyl pyridine) is prepared by living anionic polymerization in THF at -78 °C in the presence of LiCl an additive. Polystyrene macroanions were end capped with a unit of diphenyl ethylene (DPE) before adding 2-vinylpyridine (2VP) monomer. For further details please see our published articles^{1,2} The scheme of the reaction is illustrated below:




Characterization:

An aliquot of the anionic polystyrene block was terminated before addition of 2VP and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The Block copolymer composition was then calculated from ¹H-NMR spectroscopy by comparing the peak area of the 2VP proton at 8.2 ppm with the peak area of the aromatic protons of polystyrene at 6.3-7.2 ppm. The composition of the block copolymer can also be determined by titration in acetic acid/HClO₄ using crystal violet indicator. Copolymer PDI is determined by SEC.


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

¹H-NMR Spectrum of the Polymer




SEC:


Sample ID: P18226-S



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18226-S_01.volt	30,138	31,294	29,229	1.038	0.2490




P18226-S2VP



Size exclusion chromatography of poly(styrene-b-2-vinyl pyridine)
 — Polystyrene, M_n=30,000 Mw= 31,200 PI=1.04
 — Polystyrene(30,000)-b-Poly(2-vinyl pyridine)(8,500),PI=1.06

DSC thermogram for the polymer:



References:

- (1). S. K. Varshney, X. F. Zhong and A. Eisenberg Macromolecules, **1993**, 26, 701-706.
- (2). Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg Macromolecules, **1994**, 27, 7923-7927.