


Sample Name: Poly(styrene-b-4-vinyl pyridine)

Sample #: P18312-S4VP

Structure:



Composition:


$M_n \times 10^3$ S-b-4VP	PDI
44.5-b-13.0	1.13

By anionic polymerization process.

Characterization:

An aliquot of the anionic polystyrene block was terminated before addition of 4VP and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The Block copolymer composition was then calculated from 1H -NMR spectroscopy by comparing the peak area of the 4VP proton at 8.2 ppm with the peak area of the aromatic protons of polystyrene at 6.3-7.2 ppm. The composition of the block copolymer can also be determined by titration in acetic acid/ $HClO_4$ using crystal violet indicator. Copolymer PDI is determined by SEC.

SEC of the polymer:



References:

- (1). S. K. Varshney, X. F. Zhong and A. Eisenberg *Macromolecules*, **1993**, 26, 701-706.
- (2). Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg *Macromolecules*, **1994**, 27, 7923-7927.

1H -NMR Spectrum of the Polymer

