


Sample Name: **diphenyl ethylene terminated poly  
styrene**

Sample #: **P18342-SDPE**

Structure:




Composition:

Mn x 10 <sup>3</sup>	PDI
7.3	1.05
T <sub>g</sub> for PS block: 90°C	

SEC elugram of the Sample:

Sample ID: P18342--SDPE end functionalied

Concentration (mg/mL)	3.5504
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-NOV25-2013-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18342-S_01.vdt	7,241	7,601	7,445	1.050	0.0932

