


Sample Name:
Poly(4-Methoxy styrene-b-tert.Butylacrylate)

Sample #: P18350-4MeOStBuA

Structure:



Composition:

Mn x 10 ³ 4MeOS-b-tBuA	Mw/Mn (PDI)
58.0-b-40.0	1.16

Synthesis Procedure:

Poly(4- methoxy styrene-b-tBuA) is prepared by living anionic polymerization by sequence addition of 4-methoxyl styrene followed by tert.butylacrylate.

Characterization Block was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area of the 4 methoxy styrene protons at 6.3-7.2 ppm with the peak area of 4-methoxy styrene at 3.7ppm and tert.butyl at 1.4 ppm .

Solubility: Polymer is soluble in THF, acetone
Figure:¹H NMR spectrum of the sample






Figure: SEC profile of the block copolymer

Sample ID: P18350-4MeOS

Concentration (mg/mL)	2.4552
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-NOV/25-2013-0002.vcm
Column Set	3x PL 1113-6300
System	System 1




Sample	Mn	Mw	Mp	Mw/Mn	IV
P18350-4MeOs_01.vdt	58,292	62,574	62,861	1.073	0.3230



Sample ID: P18350-4MeOStBuA

Concentration (mg/mL)	5.8715
Sample dn/dc (mL/g)	0.1175
Method File	PS80K-Jan05-2014-0001.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18350P_01.vdt	98,274	113,809	120,336	1.158	0.3967

