




Sample Name: P18395-10S
10- arms Poly styrene




Mn x 10 ³ (total)	PDI
6.3	1.10
Mn of each arm: (0.6)	

Synthesis Procedure:




Linker : PBd:


H NMR:



SEC of the Polymer: (eah branch of Polystyrene)
Sample ID: P18395-1




Sample	Mn	Mw	Mp	Mw/Mn	IV
P1839 Star_ord_01.vdt	598	824	910	1.377	0.0308



Sample ID: P18395-S star

Concentration (mg/mL)	12.2959
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-Apr15-2014-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18395_01.vdt	6,249	6,932	5,924	1.109	0.0290

