



Sample Name: P18400-47S
Multi- arms Poly styrene




Core Poly butadiene




Branches of Polystyrene

Mn x 10 ³ (total)	PDI
47.0	1.06
Mn of each arm: (1.0)	

Synthesis Procedure:




Linker : PBd:




SEC of the Polymer: (eah branch of Polystyrene)


Sample ID: P18400S Star



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18400y-Star_01.vdt	47,191	49,900	48,492	1.057	0.0606



Sample ID: P18400S Star



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18400y-Star_01.vdt	47,191	49,900	48,492	1.057	0.0606

