




Sample Name: P18414-18Bd  
18- arms Poly Butadiene (rich in 1,4 addition)




HNMR of Branch




SEC of the Polymer: (eah branch of Poly butadiene)  
Sample ID: P18414-Bd Branch




Sample	Mn	Mw	Mp	Mw/Mn	IV
P18414-Bd-Branch_01.vdt	1,089	1,145	1,094	1,051	0.0997




Sample ID: P18414-Star Bd



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18414-Star_pick_out_01.vdt	16,593	18,225	17,310	1,098	0.1078



Synthesis Procedure:



Linker : PBd:

