


Sample Name: Poly(2-vinyl pyridine-b-dimethylsiloxane)

Sample #: P18682A-2VPDMS

By controlled radical process

Structure:



Composition:


$M_n \times 10^3$ 2VP-b-DMS	Mw/Mn
1.0-b-15.0	1.3

Synthesis Procedure:



Poly(2-vinyl pyridine-b-dimethylsiloxane) is synthesized by one of the following routes.

Different routes for the synthesis of poly 2 vinyl pyridine with polydimethyl siloxane:


1. Direct Anionic Polymerization by sequential addition of 2VP followed by D3 monomer




2. From the linking reaction of end functionalized polymer: For the synthesis of Block copolymer > Mn 10,000



3. Formation of first Poly 2vinyl pyridine OH terminated polymer than reacting the isolated P2VPOH polymer with a BuLi dissolved by addition of D3 in the presence of DMSO equimolar amount with aBuLi



4. By Controlled radical process:




Characterization:

Polymers were analyzed by size exclusion chromatography (SEC) and ¹H-NMR spectroscopy by comparing the peak area of the 2-vinyl pyridine proton at about 8.2 ppm with the dimethyl siloxane protons at 0.08 ppm. Copolymer PDI is determined by SEC.

Solubility:

Poly(2-vinyl pyridine-b-dimethyl siloxane) is soluble in THF, CHCl₃ and toluene

P18682A-2VPDMS



¹H NMR for the polymer:

