


Sample Name: Poly(acrylic acid)

SEC of Homopolymer:

P18755-AA

Sample #: P18755A-AA

Structure:




Composition:

Mn x 10 ³	PDI
65.0	1.6

Synthesis Procedure:

Poly(acrylic acid) is synthesized by anionic polymerization of t-butyl acrylate followed by hydrolysis of the tert. butyl group. The reaction scheme is below.



Characterization:



The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Hydrolysis: The quantitative hydrolysis of the ester is confirmed by the disappearance of tert.butyl ester absorbance at around 1370cm⁻¹.

Solubility:

Poly(acrylic acid) is soluble in THF, water, methanol, ethanol. The polymer precipitates from ether, acetone, hexane.

FTIR Spectra of Poly(tert. butyl acrylate) and poly(acrylic acid)



Size Exclusion Chromatography of In DMF

M_n = 65,000, M_w = 104,000, PI = 1.6

References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53