


Sample Name: Poly(styrene-b-ethylene oxide)

Sample #: P18781-SEO

Structure:



Composition:

$M_n \times 10^3$	PDI
23.0-b-94.0	1.16

Synthesis Procedure:

Poly(styrene-b-ethylene oxide) diblock copolymer is prepared by living anionic polymerization.


Characterization:

The molecular weight and polydispersity index (PDI) of the block copolymer are characterized by size exclusion chromatography (SEC). The composition of the block copolymer was calculated from ^1H -NMR by comparing the peak area of the phenyl polystyrene protons between 6.4 to 7.2 ppm and the ethylene oxide protons at 3.65 ppm.

Solubility:

The polymer is soluble in THF (at 35 °C), CHCl_3 , benzene, toluene, dioxane. Low molecular weight SEO with high contents of the polyethylene oxide block can also be solubilized in methanol and water.


^1H NMR spectrum of the sample




SEC profile of the block copolymer

Sample ID: P18781-SEO

Concentration (mg/mL)	18.6642
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-august 5-2014-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	M_n	M_w	M_p	M_w/M_n	IV
P18781-SEO_01(324).vdt	117,685	135,888	152,490	1.155	0.3638



Thermal analysis results


Thermal analysis was done on a TA Q100 differential scanning calorimeter at a heating rate of 20°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

The melting temperature (T_m) was taken as a maximum of the endothermic peak.


For PS block T_g : 85°C	
For PEO block	
T_g : -63°C	T_m : 61°C

DSC curves are presented on the next page.

DSC of P18780-SEO: Tm curve for PEO block:



Tg curve for PEO block:



Tg curve for PS block:

