


Sample Name:  
 **$\alpha,\omega$ -dihydroxy Terminated PolyIsoprene**

**(1,2 rich microstructure)**

Sample #: **P18803-IP2OH**

Structure:




Composition:

$M_n \times 10^3$	PDI
3.5	1.25
Functionality	>1.98
1,4 and 1,2+3,4	20:80


SEC of product:

**Sample ID: P18803-IP2OH**

Concentration (mg/mL)	0.8667
Sample conc (mg)	0.1250
Method File	PS80K-July11-2014-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18803-IP2OH_01.vdt	3,457	4,302	5,248	1.245	0.5596



**H NMR:**

