


Sample Name:
 α,ω -dihydroxy Terminated PolyIsoprene

(1,2 rich microstructure)

Sample #: **P18804-IP2OH**




Structure:



Composition:

$M_n \times 10^3$	PDI
8.5	1.14
Functionality	>1.98
1,4 and 1,2+3,4	20:80


H NMR:



SEC of product:

Sample ID: P18804-IP2OH

Concentration (mg/mL)	1.0225
Sample ch/d: (mL/g)	0.1250
Method File	PS80K-July11-2014-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18804-IP2OH_01.vdt	8,519	9,696	11,132	1.138	0.9100

