


Sample Name: **Polystyrene**

Sample #: **P19055-S**

Structure:




Composition:

Mn x 10 ³	PDI
136.0	1.10

Synthesis Procedure:

Polystyrene is obtained by living anionic polymerization of styrene as illustrated below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Solubility:

Polystyrene is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC elugram of the polymer:

Sample ID: P19055

Concentration (mg/mL)	1.5364
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-Jan22-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19055-S_01(442).vdt	136,244	150,752	134,678	1.106	1.0255