


Sample Name: Poly(styrene-b-4-vinyl pyridine)

Sample #: P19213-S4VP

Structure:



Composition:

$M_n \times 10^3$ S-b-4VP	PDI
211.5–b–14.0	1.06
Tg for PS block:	104 °C

Synthesis Procedure:

Poly(styrene-b-4-vinyl pyridine) is prepared by living anionic polymerization in THF at -78°C in the presence of LiCl an additive.

Characterization: by SEC and by $^1\text{H-NMR}$.

Purification of the obtained polymer:


Purification of the obtained polymer was carried out rigorously as follows to ensure the removal of the catalyst side product:

1. Dissolved the polymer in CHCl_3 and wash with de-ionized distilled water to remove any soluble organic catalyst side product.
2. Polymer was extracted from water with chloroform.
3. Polymer solution in CHCl_3 was dried over anhydrous sodium sulfate.
4. Solution was filtered and then was passed through a column packed with basic Al_2O_3 .
5. Solution was concentrated on rota-evaporator
6. Solution was precipitated in cold hexane and redissolved in benzene and freeze dried.
7. Dried under vacuum for 48h at 50°C .

References:

- (1). S. K. Varshney, X. F. Zhong and A. Eisenberg Macromolecules, **1993**, 26, 701-706.
- (2). Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg Macromolecules, **1994**, 27, 7923-7927.


$^1\text{H NMR}$ spectrum of the polymer:



SEC of the first block:

Sample ID: P19213-S

Concentration (mg/mL)	2.0018
Sample dv/dc (mL/g)	0.1850
Method File	PS80K-March6-2015-0000.vcm
Column Set	3x PL 11136300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19213-1_01.vcl	211,351	221,979	219,188	1.050	0.6136