


Sample Name: Poly (styrene -b- acrylic acid)

Sample #: P19263-SAA

P19263-StBuA

Structure:



Composition:

Mn x 10 ³ PS-b-PAA	PDI
18.5-b-2.5	1.15

Synthesis Procedure:

Poly (styrene-b-acrylic acid) is prepared by living anionic polymerization with sequence addition of styrene followed by t-butyl acrylate and hydrolysis of the t-butyl group.

Characterization:

An aliquot of the polystyrene block was terminated before addition of t-butyl acrylate and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The hydrolysis of the tert. butyl ester to acid was followed by FT-IR spectroscopy by disappearance of characteristic absorbance at 1362cm⁻¹ of tert.butyl group.


Solubility:

Poly (styrene-b-acrylic acid) is soluble in THF, dioxane and also in methanol (depending on the compositions with a short segment of polystyrene with long segment of poly acrylic acid). The polymers is precipitated out from ether, hexane.


SEC for the sample:

Sample ID: P19263-1


Concentration (mg/mL)	1.5659
Sample稀釋 (mL/g)	0.1850
Method File	PS80K-April29-2015-0000.vcm
Column Set	3xPL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19263-1_01.vdt	18,557	20,584	18,670	1.109	0.5372



¹H NMR for the polymer:



References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, R. Fayt, S. K. Varshney, and C. Jacobs Eur. Pat. Appl., Jan 16, 1991 Eur.Pat.408420
Patent Assignees- Atochem S.A France. CA Vol 114, 26, 247998." Star Block Copolymers based on Acrylates and Methacrylates and their Manufacture process".
3. Ph. Teyssie, R. Fayt, and S. K. Varshney, Eur. Pat. Appl. Dec. 12, 1990. Eur. Pat.402204 Patent Assignees-Norsolor S.A. France. CA Vol 114, 20, 186314."Catalyst for the the Anionic Living Polymerization (Meth)acrylates".