


Sample Name: **Poly (methyl methacrylate)**

Different microstructure

Sample #: **P19327E-MMA**

Structure:



Composition:

$M_n \times 10^3$	PDI
496.5	1.7
Syndio : Hetero : Isotactic	60:35:5

Synthesis Procedure:

Poly (methyl methacrylate) is obtained by RAFT process.

Characterization:

Tacticity of the polymer was determined by ¹H NMR. The molecular weight and polydispersity index (PDI) were obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.


Solubility:

The polymer is soluble in THF, CHCl_3 , toluene and dioxane. The polymer precipitates from cold methanol and ethanol.

T_g vs MW for selected atactic PMMA:


$M_n \times 10^3$	T_g (°C)	$M_n \times 10^3$	T_g (°C)
1.1	51	36	98
2.5	76	55	111
5.0	91	70	107
15	101	127	115
19	107	230	114
29	96	700	121

¹H NMR spectrum of PMMA:



SEC elugram of PMMA homopolymer:
Sample ID: P19327E_MMA

Concentration (mg/mL)	1.0354
Sample conc (mL/g)	0.0840
Method File	PS80K-June30-2015-0000.vcm
Column Set	3xPL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersi	Intrinsic Viscosity (dL/g)
P19327E-MMA_01.vct	496,418	848,404	605,721	1.709	5.5953

DSC:

T_g of atactic poly methyl methacrylate as function of molecular weight

