


Sample Name: **Polybutadiene (1, 4-rich microstructure)**  
 Sample #: **P19351-Bd**

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup>	PDI
5.0	1.09

**Synthesis Procedure:**

The 1,4-addition polybutadiene was prepared by anionic living polymerization of butadiene in non-polar media.


**Characterization:**

By GPC and HNMR.

**Microstructure:** The ratio between 1,4- and 1,2-addition was calculated by <sup>1</sup>H NMR spectroscopy.

**Solubility:**


The polybutadiene is soluble in DMF, THF, toluene, hexane, cyclohexane and CHCl<sub>3</sub>. It precipitates from methanol, ethanol and water.



**SEC of Sample:**

**Sample ID: P19351-Bd**

Concentration (mg/mL)	1.7678
Sample conc (mL/g)	0.1250
Method File	PS80K-June30-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19351-Bd_01.vdt	5,010	5,288	4,987	1.055	0.8618

**HNMR of Sample:**

