


Sample Name: **Polystyrene**

Sample #: **P19360-S**

Structure:




Composition:

Mn x 10 ³	PDI
1,000.0	1.05

Synthesis Procedure:

Polystyrene is obtained by living anionic polymerization of styrene as illustrated below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Solubility:

Polystyrene is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC elugram of the polymer: run in DMF

Sample ID: P19360-S

Concentration (mg/mL)	0.2704
Sample chkb (mL/g)	0.1850
Method File	PS80KJune30-2015-0000.hcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19360-S_01.volt	1.008 e 6	1.050 e 6	1.010 e 6	1.041	11.2553