


Sample Name: Poly (styrene-b-methyl methacrylate) (*polymethylmethacrylate rich in syndiotactic contents > 78%*)
Sample #: P19377-SMMA

Structure:



Composition:

Mn x 10 ³ S-b-MMA	PDI
725.0-b-736.0	1.35
T _g for PS block: 107°C	T _g for PS block: 133°C

Synthesis Procedure:

By anionic Polymerization.


Characterization:

BY SEC and HNMR analysis.

Solubility:

Poly (styrene-b-methyl methacrylate) is soluble in THF, toluene, dioxane and CHCl₃. This polymer readily precipitates from methanol, ethanol, hexanes and water.


¹H-NMR Spectrum of the Polymer:



SEC of Sample:


Sample ID:P19377P-SMMA

Concentration (mg/mL)	0.2148
Sample dn/dc (mL/g)	0.1230
Method File	PS80K-June30-2015-0000.vsm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersit	Intrinsic Viscosity (dL/g)
P19377-SMMA_01.vcl	1.461 e 6	1.995 e 6	1.807 e 6	1.366	12.620

Thermogram of the sample



References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
3. Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney *Makromolekular Chemie, Macromol. Symp.*, 1990, 32, 61-73.
4. S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph. Teyssie *Macromolecules*, 1990, 23, 2618-2622.
5. R. Jerome, R. Forte, S. K. Varshney, R. Fayt, and Ph. Teyssie "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.