


Sample Name: **Poly (methyl methacrylate)**
Atactic polymer

Sample #: **P19393-MMA**

Structure:



Composition:

Mn x 10 ³	PDI
225.5	1.4
Syndio : Hetero : Iso	42 : 52 : 6
T _g	104°C

Synthesis Procedure:

Tacticity of the poly(methyl methacrylate) is tailored by anionic polymerization of MMA monomer in different polarity solvents mixture and using different ligands.

Characterization:


Tacticity of the polymer was determined by ¹H NMR. The molecular weight and polydispersity index (PDI) were obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

Solubility:


The polymer is soluble in chloroform.

¹H NMR spectrum of PMMA:




SEC elugram of PMMA homopolymer:
Sample ID: P19393-MMA

Concentration (mg/mL)	0.4707
Sample dn/dc (mL/g)	0.0840
Method File	PS80K-June30-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF




Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19393-PMMA_01.vdt	225,587	323,295	318,435	1.433	3.2407

DSC thermogram of the polymer




Thermograms of PMMA:


(a) syndiotactic >79%




(b) syndiotactic >85%



(c) isotactic >97%



(d) atactic



Summary of DSC results for PMMA of different tacticity:

PMMA microstructure	Tacticity Syndio : Iso : Hetero	T_g (°C)
Syndiotactic >79%	79 : 19 : 2	120
Syndiotactic >85%	86 : 0 : 14	123
Isotactic >97%	0 : 97 : 3	44
Atactic	56 : 6 : 38	97