


Sample Name: Poly (styrene-b-methyl methacrylate) (*polymethylmethacrylate rich in syndiotactic contents > 78%*)
Sample #: P19453P-SMMA

Structure:



Composition:

Mn x 10 ³ S-b-MMA	PDI
1,350.0-b-722.0	1.10
T _g for PS block: 107°C	T _g for PS block: 133°C

Synthesis Procedure:

By anionic polymerization

Characterization:


BY SEC and HNMR

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 15°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

Solubility:

Poly (styrene-b-methyl methacrylate) is soluble in THF, toluene, dioxane and CHCl₃. This polymer readily precipitates from methanol, ethanol, hexanes and water.


¹H-NMR Spectrum of the Polymer:



SEC of Sample: run in DMF

SAMPLE ID: P19453-SMMA run in DMF

Conc (mg/mL)	2.3920
dν/dc (mL/g)	0.1140
Method	ps80kJuly292015-0000.vcm
Solvent	DMF w 0.03M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P19453-SMMA_01.vdt	2.071 e 6	2.427 e 6	2.498 e 6	1.172	2.3230

References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
3. Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney *Makromolekulare Chemie, Macromol. Symp.*, 1990, 32, 61-73.
4. S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph. Teyssie *Macromolecules*, 1990, 23, 2618-2622. and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.