




## SEC of polybutadiene fist block:

Sample ID:P19479-Bd

Concentration (mg/mL)	0.1602
Sample dn/dc (mL/g)	0.1250
Method File	PS80K-June30-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF




Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19479-1_01.vdt	26,516	42,013	34,834	1.594	3.0079

## SEC of diblock copolymer:

Sample ID:P19479-BdIP

Concentration (mg/mL)	1.4645
Sample dn/dc (mL/g)	0.1250
Method File	PS80K-June30-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19479-2_01.vdt	267,954	317,869	272,392	1.104	10.4889