


Sample Name: Deuterated Polystyrene (d<sub>8</sub>)

Sample #: P19911A-dPS

**Structure:**




**Composition:**

Mn x 10 <sup>3</sup>	PDI
525.0	1.4

**Synthesis Procedure:**

Deuterated polystyrene-d<sub>8</sub> is obtained by controlled radical polymerization of styrene-d<sub>8</sub> as illustrated below:



**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


**Solubility:**

Deuterated polystyrene-d<sub>8</sub> is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes.

**SEC elugram of Homopolymer:**

**P19911A-dPS**

Conc (mg/mL)	2.0798
dn/dc (mL/g)	0.1650
Method	ps80k-May2016-0002.vcm
Solvent	DMF w/0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P19911A-dPS_01.vdt	525,112	732,081	590,656	1.394	1.1054