


Sample Name: Poly(methyl methacrylate)

Different microstructure

Sample #: P20206-MMA

Structure:



Composition:

Mn x 10 ³	PDI
370.0	1.25

Syndio : Hetero : Iso	65:32:3
T _g	99 °C

Synthesis Procedure:

Tacticity of the poly(methyl methacrylate) is tailored by anionic polymerization of MMA monomer in different polarity solvents mixture and using different ligands.

Characterization:


Tacticity of the polymer was determined by ¹H NMR. The molecular weight and polydispersity index (PDI) were obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

Solubility:

The polymer is soluble in chloroform.


¹H NMR spectrum of PMMA:



SEC elugram of PMMA homopolymer:

Sample ID: P20206-MMA


Concentration (mg/mL)	0.4901
Sample ch: c (mL/g)	0.0840
Method File	PS80K-April13-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF




Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
_P20206-MMA_01.vdt	370,023	462,492	494,770	1.250	2.2955

Thermograms of PMMA:


(a) syndiotactic >79%



(d) atactic



(b) syndiotactic >85%



Summary of DSC results for PMMA of different tacticity:

<i>PMMA microstructure</i>	<i>Tacticity Syndio : Iso : Hetero</i>	<i>T_g (°C)</i>
Syndiotactic >79%	79 : 19 : 2	120
Syndiotactic >85%	86 : 0 : 14	123
Isotactic >97%	0 : 97 : 3	44
Atactic	56 : 6 : 38	97

(c) isotactic >97%

