


Sample Name: Deuterated Polystyrene (d₈)- ethylene oxide (protonated)

Sample #: P2780-dPSEO

Structure:



Composition:

Mn x 10 ³ (dPS-b-EO)	PDI
189.0-b-2.0	1.06
T _g for dPS block 100°C	
T _m , T _c T _g for PEO block Not observed	


Synthesis Procedure:

Deuterated Poly(styrene-b-ethylene oxide) diblock copolymer is prepared by living anionic polymerization.


Characterization:

The molecular weight and polydispersity index (PDI) of the block copolymer are characterized by size exclusion chromatography (SEC). The composition of the block copolymer was calculated from ¹H-NMR by comparing the peak area of the phenyl polystyrene protons between 6.4 to 7.2 ppm (indicating about 1% protonated fraction) and the ethylene oxide protons at 3.65 ppm. This is given an approximate analysis. The yield of the polymer from the theoretical amount of deuterated styrene and protonated ethylene oxide monomer calculate also the compositions required.

D NMR of the polymer:




HNMR spectrum of the sample:




SEC profile of the product:

P2780-dPSEO



DSC thermogram for dPS block:



References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. S. K. Varshney, Jian-Xin Zhang. US patent 7009,033 B3 2006.