


SEC of Sample -SMMA:


P10345-SMMA



Size Exclusion Chromatography of Poly Styrene-b-MMA

— PS block $M_n = 700,000$, $M_w = 486,000$, $M_w/M_n = 1.08$
PS-b-MMA: $M_n = 700,000$ -b- $1200,000$ PI: 1.4

Thermogram for the sample



References for further information:


1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
3. Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney *Makromolekular Chemie, Macromol. Symp.*, 1990, 32, 61-73.
4. S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph. Teyssie *Macromolecules*, 1990, 23, 2618-2622.

Sample Name: Poly(styrene-b-methyl methacrylate)

(polymethylmethacrylate rich in syndiotactic contents > 78%)

Sample #: P10345-SMMA

Structure:



Composition:

$M_n \times 10^3$ S-b-MMA	PDI
700.0-b-1200.0	1.4
T_g for PS block: 107°C	T_g for PMMA block: 132 °C
dn/dc in THF at 35 °C	0.127
Mn values obtained from LS detector on line:	1,600,000

Synthesis Procedure:

By anionic process: For further details please see our published articles.¹⁻⁵

Characterization: Polymer analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area of the poly(methyl methacrylate) protons (eg.—OCH₃ at 3.6ppm) with of aromatic protons of polystyrene at 6.3-7.2 ppm. Copolymer PDI is determined by SEC. Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

¹H-NMR Spectrum of SMMA:

