


Sample Name: **Polystyrene**

Sample #: **P2934-S**

Structure:




Composition:

$M_n \times 10^3$	PDI
6.1	1.05

Synthesis Procedure:

Polystyrene is obtained by living anionic polymerization of styrene as illustrated below:



Characterization:


The molecular weight and polydispersity index (PDI) were obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the sample was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of $10^\circ C/min$. The inflection glass transition temperature (T_g) has been considered.

Solubility:

Polystyrene is soluble in DMF, THF, toluene and $CHCl_3$. It precipitates from methanol, ethanol, water and hexanes.

SEC of Homopolymer:



Size Exclusion Chromatography of Polystyrene:

$M_n = 6100$, $M_w = 6400$, $PI = 1.05$

T_g of polystyrene as function of molecular weight

