


**Sample Name:**Poly(styrene-*b*-hydroxypropyl methacrylate)

Thermogram for PS block:

**Sample #: P3310-SHPMA****Structure:****Composition:**

Mn x 10 <sup>3</sup> S-b-HPMA	Mw/Mn (PDI)
22.0-b-7.0	1.14

**Glass transition temperature at a glance**

T <sub>g</sub> for PS block	101°C
T <sub>g</sub> for HPMA	Not distinct

**Synthesis Procedure:**

Poly(styrene-*b*-hydroxy propyl methacrylate) is prepared by living anionic polymerization by sequence addition of styrene followed by 2-hydroxypropyl methacrylate and deprotection of the OH group.

**Characterization:**

An aliquot of the polystyrene block was terminated before addition of 2-hydroxypropyl methacrylate and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy by comparing the peak area of the styrene protons at 6.3-7.2 ppm with the peak area of 2-propyl methacrylate at ppm. Block copolymer PDI is determined by SEC.

**Thermal analysis:**

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T<sub>g</sub>).

**Solubility:**

Poly(styrene-*b*-hydroxy propyl methacrylate) is soluble in DMF.

