


**Sample Name:** Deuterated Polystyrene ( $d_8$ )

**Sample #:** P3620A-dPS

**Structure:**




**Composition:**

$M_n \times 10^3$	PDI
14.5	1.9

**Synthesis Procedure:**

Deuterated polystyrene- $d_8$  is obtained by living anionic polymerization of styrene- $d_8$  as illustrated below:



**Characterization:**


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.

**Solubility:**

Deuterated polystyrene- $d_8$  is soluble in DMF, THF, toluene and  $CHCl_3$ . It precipitates from methanol, ethanol, water and hexanes.

**SEC of Homopolymer:**

**P3620A-dPS**



Size exclusion chromatograph of deuterated polystyrene( $d_8$ ):

$M_n=14500$   $M_w=27500$ ,  $PI=1.9$